

## RAPID DECOLORIZATION OF ACID ORANGE II IN AQUEOUS SOLUTION BY WASTE IRON OXIDE PARTICLES

M.A.K. Azad<sup>1</sup>, S.S.S. Shean<sup>2</sup> and Fahmida Gulshan<sup>3</sup>

<sup>1-3</sup>Department of Materials and Metallurgical Engineering (MME)  
Bangladesh University of Engineering and Technology (BUET), Bangladesh

<sup>1</sup>makazad005@yahoo.com, <sup>2</sup>sejan29@gmail.com, <sup>3</sup>fahmidagulshan@mme.buet.ac.bd

**Abstract-** Discharges of highly colored dye effluents in natural water constitute a significant burden on the environment. The solar driven photo-Fenton process based on Fe(III)-oxalate complexes, an important advanced oxidation process [AOP] technology, has been attracting growing attention for the decomposition of organic dyes. Such process is based on the light enhanced generation of the highly reactive hydroxyl radicals, which oxidize the organic matter in solution and convert it completely into water CO<sub>2</sub> and inorganic compounds. In the present study, the effectiveness of iron oxide wastes generated in steel re-rolling mills to decompose a synthesized dye [Acid Orange II] under UV illuminations was investigated. The decomposition of dye by iron oxide suspension at natural solution pH was investigated. The experiments were carried out by varying amount of iron oxide catalyst (0.1–1 g/100mL) in oxalic acid concentration of 1mM/100 mL solution and with initial dye concentration of 0.1 mM/100mL solution. The optimum catalyst dose was found to be 0.05 g/100mL solution. From this study it was found that iron oxide wastes could be useful in treating dye wastes thus can play an important role to minimize both iron oxide and dye wastes.

**Keywords:** Photocatalytic activity, Photo-ferrioxalate process, Acid Orange II.

### 1. INTRODUCTION

Water is an indispensable requirement of life, as well as industries which are working for the betterment of human life and health. Industrialization made a deep impact on human health directly or indirectly creating environment (air, water, soil) polluted by releasing wastes and untreated wastewater, into the environment. In many countries, most of the textile industries are using color materials like dyes and pigments, and effluents are released to canal, river, and sea without further treatments and purifications. In presence of these organic compounds, water becomes unusable for practical uses. Colorants – dyes and pigments – are a growing pollution problem in the industrial and household wastewater as a result of their extensive use and relative stability towards degradation. Dyes undergo chemical changes as well as biological changes in the aquatic system, consume dissolved O<sub>2</sub> and thus disturb the aquatic eco-system. The untreated dyes in effluents from textile and coloring are a group of hazardous chemicals as well as major sources of water pollution. It is therefore necessary to treat the water containing color dyes and other organic compounds to discharge them.

Due to the complex aromatic structure and stability of these dyes, conventional biological pre-treatment methods are ineffective for degradation. Also low efficiency and low reaction rate are associated with these methods caused the methods to be ineffective. The typical dyestuff treatment includes physical and chemical methods, such as coagulation/flocculation, activated carbon, adsorption and bio-treatment,

ozonation, sodium hypochlorite treatment, photochemical decolourization. Amongst the disadvantages of these methods are either formation of large amounts of sludge, or generation of toxic byproducts (aromatic amines) when the degradation is incomplete, i.e. without the opening of the aromatic ring of the dye molecule. These limitations of conventional wastewater treatment methods can be overcome by the application of the advanced oxidation processes (AOP), which has the unique ability to fully mineralize the dyes, including the opening of the aryl ring.

AOP in a broad sense, refers to a set of chemical treatment procedures designed to remove organic (and sometimes inorganic) materials in water and waste water by oxidation through reactions with hydroxyl radicals ( $\cdot\text{OH}$ ). AOPs such as the Fenton reaction have been found to be very effective for removing organic pollutants from wastewater. The Fenton system involves the generation of  $\cdot\text{OH}$  which can degrade most organic compounds to CO<sub>2</sub> and H<sub>2</sub>O due to their high oxidation potential ( $E^0 = +2.80\text{ V}$ ) [1]. In real-world applications of wastewater treatment, however, this term usually refers more specifically to a subset of such chemical processes that employ ozone (O<sub>3</sub>), hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>) and/or UV light to increase the efficiency of  $\cdot\text{OH}$  generation [2]. In these reactions, H<sub>2</sub>O<sub>2</sub> is added as the direct source of  $\cdot\text{OH}$ . However, H<sub>2</sub>O<sub>2</sub> is an extremely reactive compound and does not survive in nature for long, limiting the usefulness of Fenton and Fenton-like systems for the degradation of organic matter in a natural environment. Other AOPs such as ozonation and ozone

related processes ( $O_3/H_2O_2$ , UV/ $O_3$ ), heterogeneous photocatalysis ( $TiO_2/UV$ ), homogeneous photocatalysis (Fenton and Fenton-like processes) and electrochemical oxidation are considered as the most efficient for pesticide degradation in water but these still have not been put into commercial use on a large scale (especially in developing countries) even up to today mostly because of the relatively high costs.

Photophoroxalate system combination of Iron Oxide (IO) and polycarboxylic acids (such as OA) can form a photochemical system to give a photo-Fenton-like reaction without the addition of  $H_2O_2$ , and with much higher quantum efficiency than with  $Fe(OH)^{2+}$  or IO alone [3]. Since the polycarboxylic acids are also abundant in the natural environment, this photochemical oxidation process can directly utilize natural materials (IO and OA) in combination with UV, to decompose organic pollutants economically. It is therefore meaningful to investigate the photodecomposition of organic pollutants in the IO-polycarboxylate complex system to better understand the transformation of organic pollutants [4]. IO is used as catalyst. The structures of the IO are well defined, and particularly interesting, determine the activities for the degradation of organic substrates. IOs are semiconductors with a band gap of 2.2 eV [5]. Thus, it can be photoexcited by light for the decomposition of organic pollutants in waters [6] and the splitting of  $H_2O$  to extract hydrogen energy or disinfect the water. Apparently, poorly crystalline IOs release iron ions more readily than their good crystalline counterparts particularly in acidic media. For the photo fenton reaction, the size of IO particles is an important parameter. The nanosized IOs are stronger absorptive and exhibit improved catalytic activity because of their large surface area which potentially provides more active sites for the generation of  $\cdot OH$  [7]. OA is one of the most active polycarboxylic acids, and has been reported by Li et al. [1], than other carboxylic acids such as citric, tartaric, malonic, malic and succinic acid. The photochemistry of  $Fe^{3+}$ -oxalate complexes has been studied by many workers [8] and  $Fe^{3+}$ -oxalate complexes are known to exhibit strong ligand-to-metal charge absorption bands in the near-UV and visible region.

During the photochemical reaction of  $Fe^{3+}$ -oxalate complexes under UV/sunlight, OA is first adsorbed on the surface of the IO in suspension, forming  $[Fe^{3+}(C_2O_4)_n]^{(2n-3)-}$ . This complex can then be excited to form  $[Fe^{2+}(C_2O_4)_{(n-1)}]^{(4-2n)-}$  and  $\cdot C_2O_4^-$ . Then  $C_2O_4^-$  is readily transformed to the carbon-centered radical  $\cdot CO_2^-$  [9], from which the excited electrons are transferred to the adsorbed  $O_2$ , forming superoxide ions  $\cdot O_2^-$ .  $Fe^{3+}$  can react with  $\cdot O_2^-$  to form  $O_2$  and  $Fe^{2+}$ . Then  $Fe^{2+}$  reacts with  $\cdot O_2^-$  and  $\cdot OH$  to form  $H_2O_2$  in acidic solution with  $Fe^{3+}$  and  $Fe^{2+}$  is reoxidized to  $Fe^{3+}$  in the presence of  $O_2$ . After  $H_2O_2$  is formed,  $\cdot OH$  can be generated by the reaction of  $Fe^{2+}$  with  $H_2O_2$ . The formation of  $\cdot OH$  in the  $Fe^{3+}$ -oxalate system and in  $H_2O_2$  has been confirmed by photochemistry [10]. The  $\cdot OH$  radicals attack firstly N=N bond and then ring to decompose into inorganic materials [11].

In this study, Acid Orange II (AOII) was selected as a model organic pollutant and its degradation was studied

in the presence of mill scale (waste iron oxides from steel plants) in oxalate solution under UV illumination.

## 2. EXPERIMENTAL

IO was ball milled to produce fine particles to increase the reactive surface area. The crystalline phases of IO samples were determined by X-ray powder diffraction (XRD) with Monochromatic  $CuK\alpha$  radiation.

The parent solution of AOII of concentration 1M was prepared with distilled water. Solutions of required concentration were then prepared from parent solution for particular experiment. The photodegradation of AOII was carried out using two 8W black light lamps with the main emission at 365 nm. The sample suspension was formed by adding varying amounts of IO to 100 ml of aqueous solution containing AOII and OA. Before photoreaction, the suspension was magnetically stirred in the dark for 30 minute to establish an adsorption-desorption equilibrium. The various aqueous suspensions were then illuminated by UV while being magnetically stirred. At the given time intervals, the analytical samples were withdrawn from the suspension into a small plastic bottle and then stored in dark for further analysis.

The absorbance spectrum in each experiment was determined from 200 to 600 nm with a UV-vis spectrophotometer and the degradation of AOII was recorded by monitoring the absorbance intensity of solution samples at their maximum absorbance at  $\lambda=484$  nm as a function of illumination time. The photodegradation efficiency of AOII was calculated by using the following formula.

$$\text{Photodegradation efficiency} = \frac{C_0 - C_t}{C_0} \times 100$$

Where,  $C_0$  and  $C_t$  are initial and final absorbance intensity of AOII solution after time t respectively.

## 3. RESULTS AND DISCUSSION

The chemical formula of AO II is shown in Fig. 1. The XRD patterns of the samples were interpreted using ICDD database. The XRD pattern of the sample collected from steel re-rolling mill, showed major phases of hematite ( $\alpha-Fe_2O_3$ ), magnetite ( $Fe_3O_4$ ) and wustite ( $FeO$ ). To determine the wavelength at which maximum absorbance intensity is occurred, absorbance spectra of AOII solution were monitored using UV-vis spectrophotometer. It is found that AOII has five absorption peaks in which two peaks in visible region and three in ultraviolet region but maximum absorbance occurred at wavelength of 484 nm (Fig. 2). In visible region, a major peak locates at 484nm and a shoulder peak locates at 430nm due to the hydrazone form and azo form of AOII, respectively. The other three peaks in ultraviolet region are assigned to the aromatic ring, among which the peaks at 228nm and 310nm in ultraviolet region are ascribed to the benzene and naphthalene rings of the dye, respectively [11].




Fig.1: Chemical formula of AO II




Fig.2: Absorption Spectra of AOII

### 3.1 Degradation behavior of AOII

To determine the degradation behavior of AOII, 1 mM dye solution with 1 mM OA and 1g IO was stirred in dark for 30 minute and then UV illumination was applied. The samples were collected after 10 minute interval and then absorbance spectra were monitored using UV-Vis spectrophotometer. Absorption peaks at 484nm and 430nm decreased rapidly as the reaction proceeded (Fig. 3) because the  $\cdot\text{OH}$  radical firstly attacked azo groups and destructed the  $\text{N}=\text{N}$  bond [11]. And absorption peaks at 310nm and 228nm related to the naphthalene and benzene respectively, gradually decreased.





Fig. 3. Absorption Spectra of AOII showing degradation behavior

### 3.2 Effect of Various Parameters on Degradation of AOII

100 ml AOII ( $C_0=0.1$  mM) solution was stirred in dark and no degradation occurred after 1 hour. But while UV illumination was applied, degradation was considerable (Fig. 4) as UV illumination provided activation energy required for bond breaking. After 50 minutes absorbance intensity increased (Fig. 4). It may be due to the experimental errors. Again 100 ml AOII ( $C_0=0.1$  mM) solution with 1 mM OA was stirred in dark and a little degradation occurred after 35 minute. But while UV illumination was applied, the degradation rate increased rapidly (Fig. 4) since UV illumination provided sufficient energy to break OA to form  $\text{H}_2\text{O}_2$  and then  $\cdot\text{OH}$  which enhanced the degradation.

Again 100 ml AOII ( $C_0=0.1$  mM) solution with 0.5gm IO was stirred in dark for 30 minutes and then UV illumination was applied. The degradation rate was very much slow in dark but rapidly increased after UV illumination (Fig. 4). The phototreatment (UV illumination) of solid IO can accelerate the recycling of  $\text{Fe(II)/Fe(III)}$ , as illustrated by following equation and produce  $\cdot\text{OH}$  which degrades AOII. [7].



Again 100 ml AOII solution ( $C_0=0.1$  mM) with 1.0 mM OA and 0.5 gm IO was stirred in dark. The absorbance intensity decreased up to 30 minutes and then increased and again decreased after 40 minutes (Fig. 4). Sometimes higher absorbance/concentration was noticed due to the intermediaries' formation. But while UV illumination was applied on solution of same concentration and composition, uniform and gradual degradation occurred. Maximum degradation occurred in this case (Fig. 4).




Fig. 4. Effect of various parameters on degradation of AOII ( $C_0=0.1$  mM).

The percentage of degradation of 0.1 mM AOII solution is summarized in Table 1.

Table 1: Degradation percentage in various conditions

Reaction Condition	Degradation (percentage)
Dark	0.4
UV	9.5
1 mM OA + dark	1.8
0.5gm IO + UV	21.2
1 mM OA+UV	30.1
1mM OA+0.5gm IO + dark	15.0
1mM OA+0.5gm IO +UV	35.29

### 3.3 Effect of IO Catalyst

To investigate the effect of IO as catalyst, 100 ml AOII ( $C_0 = 0.1\text{mM}$ ) solution with 1.0 mM OA and varying amounts of IO was stirred first in dark for 30 min and then under UV illumination. It was noticed that very low degradation occurred for 0.05 gm IO in dark. But while UV illumination was applied, degradation increased rapidly and highest degradation occurred after 80 minutes (Fig. 5). Because IO acted as catalysts and enhanced  $\cdot\text{OH}$  production hence increased degradation rate. But with increasing IO content although initial degradation rate was high but actual efficiency decreased. For 0.1 gm IO degradation was considerable in dark and degradation was very high after UV illumination. Hence maximum degradation occurred in short time but overall efficiency was lower than that for 0.05 gm after 80 minutes. For further increasing of IO, though initial degradation was high but actual efficiency was much lower. The overall results are shown in (Fig. 5).

But with higher content of IO, degradation becomes lower due to the intermediaries formation. Agglomeration can occur for which active sites for reaction decreases. Also at high amount of catalyst, the opacity, turbidity of the suspension, and light scattering of catalyst particles are increased. This tends to decrease the passage of irradiation through the sample [13].

The photodegradation efficiency of AOII for various amount of IO with 1 mM OA was investigated and it was found that the efficiency was highest for 0.05 gm IO for above reaction conditions (Fig. 6).

## 4. CONCLUSION

The photodegradation of AOII was investigated with varying amounts of IO and with or without UV and AO. The following results are concluded.

1. For the highest photodegradation efficiency, the combined application of OA, IO and UV illumination is needed.
2. Stirring is needed to homogenize the solution and to facilitate adsorption reaction which enhance the photodegradation efficiency.
3. UV illumination excites IO catalyst and enhance degradation rate.

4. Absorbance/concentration of residual dye solution should be measured instantly as the degradation reaction continues in sunlight even in dark.

For the dye degradation optimum amount of IO (catalyst) should be determined. Otherwise degradation rate becomes lower and the process is very much inefficient. Optimization of IO is accomplished with respect to volume and concentration of dye solution. For degradation 100 ml AOII solution ( $C_0 = 0.1\text{mM}$ ) with 1 mM OA, optimum IO is 0.05 gm.




Fig.5: Effect of IO on degradation of AOII




Fig.6: Photodegradation efficiency of AOII

## 5. REFERENCES

- [1] D.L.Sedlak, A.W.Andren, "Aqueous-phase oxidation of polychlorinated biphenyls by hydroxyl radicals", *Environ.Sci.Technol.* 25 (1991) 1419-1427.
- [2] W.Z.Tang, R.Z.Chen, "Decolorization kinetics and mechanisms of commercial dyes by  $\text{H}_2\text{O}_2$ /iron powder system", *Chemosphere* 32 (1996) 947-958
- [3] C.Siffert, B.Sulzberger, "Light induced dissolution of hematite in the presence of oxalate. A case study", *Langmuir* 7 (1991) 1627-1634.
- [4] F.B.Li, J.J.Chen, C.S.Liu, J.Dong, T.X.Liu, "Effect of iron oxides and carboxylic acids on photochemical

- degradation of bisphenol A”, *Biol Fertil Soils* 42 (2006) 409-417.
- [5] A. Kay, I. Cesar, and M. Gratzel, “New benchmark for water photooxidation by nanostructured  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> films,” *Journal of the American Chemical Society*, vol. 128, no. 49, pp. 15714–15721, 2006.
- [6] S. K. Maji, N. Mukherjee, A. Mondal, and B. Adhikary, “Synthesis, characterization and photocatalytic activity of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> nanoparticles,” *Polyhedron*, vol. 33, no. 1, pp. 145–149, 2012.
- [7] ChuanWang, Hong Liu, and Zhimin Sun “Heterogeneous Photo-Fenton Reaction Catalyzed by Nanosized Iron Oxides for Water Treatment” *Hindawi Publishing Corporation International Journal of Photoenergy* Vol. 2012, Article ID 801694, pp.10 doi:10.1155/2012/801694
- [8] G.V.Buxton, C.L. Greenstock, W.P.Helmen, A.B.Ross, “Critical Review of rate constants for reactions of hydrated electrons” *Chemical Kinetic Data Base for Combustion Chemistry*. Part 3: Propane, *J. Phys Chem. Ref. Data* 17 (1988) 513
- [9] J.Bandara, J.Kiwi, Fast kinetic spectroscopy, decoloration and production of H<sub>2</sub>O<sub>2</sub> induced by visible light in oxygenated solutions of the azo dye Orange II, *New J.Chem.* 23 (1999) 717-724.
- [10] Sunil Kommineni, Ph.D,Jeffrey Zoeckler,Andrew Stocking, P.E.,Sun Liang, Ph.D,Amparo Flores,Michael Kavanaugh, Ph.D., P.E.”*Advanced Oxidation Process*”.
- [11] Y. Mu, H.Q. Yu, J.C. Zheng, S.J. Zhang, TiO<sub>2</sub>-mediated photocatalytic degradation of Orange II with the presence of Mn<sup>2+</sup> in solution, *J. Photochem. Photobiol. A*163 (2004) 311–316
- [12]Xiaoliang Liang,Yuanhong Zhong, Sanyuan Zhu, Jianxi Zhu, Peng Yuan, Hongping He, Jing Zhang
- [13] R. M.Mohamed, I. A. Mkhalid, E. S. Baeissa, and M. A. Al-Rayyani “Photocatalytic Degradation of Methylene Blue by Fe/ZnO/SiO<sub>2</sub> Nanoparticles under Visiblelight.” *Hindawi Publishing Corporation, Journal of Nanotechnology* Vol. 2012, Article ID 329082, pp 5, doi:10.1155/2012/329082.